

## **Roller/Brush Rubber<sup>®</sup>**

### **Cold Fluid Applied Rubber Membrane System**

### **Technical Datasheet**

#### **CSI Div. 07**

07 14 16 Cold Fluid Applied Waterproofing

#### **Product Description:**

Cantex Roller/Brush<sup>®</sup> is a ready to use fast setting, cold applied, modified asphalt emulsion system using exact formulated polymers providing unique elastomeric performance. It can be installed where solvents and heat are not allowed. Its formulation is designed for one-coat, seamless applications by roller or brush.

#### **Typical Applications:**

- ❖ Below grade, concrete or CMU exterior foundations
- ❖ Primary and secondary containment tanks
- ❖ Water fountains, ponds and water features
- ❖ Waste water treatment tanks and reservoirs
- ❖ "Sandwich slab" construction

#### **Advantages:**

- ❖ Zero VOC's
- ❖ No "hot pots" or trailers
- ❖ Cost Efficient – reduced application times
- ❖ One component, ready to use
- ❖ 1200% Elongation
- ❖ Self-healing
- ❖ Monolithic without seams
- ❖ Resistant to many chemicals (contact Cantex for complete listing)

#### **Substrate Preparation:**

- ❖ Substrates must be free of all dirt, dust, grease, oil, sealers, curing compounds, form release agents, laitance and loose toppings.
- ❖ Only proceed with application when the temperatures remain between 40°F and 90°F (4°C and 32°C) and protect from freezing for 24 hours after application.
- ❖ All surfaces to be coated should be dry (damp is acceptable with no standing water). Hot surfaces should be cooled and shaded while cold surfaces should be heated and sheltered.
- ❖ For proper adhesion, concrete substrates must have a minimum CSP-3 Concrete Surface Profile as per ICRI Guideline No. 310.2-1997 (Formerly Guideline No. 03732).

- ❖ All loose particles and/or flaking coatings must be removed by sandblasting, water-blasting or other mechanical means.
- ❖ All detail work and tape application must be completed before application of membrane can be started.

#### **Mixing:**

For best results, mechanically mix at slow speed with a 3/4" drill and mixing paddle. Mix at slow speeds (not exceeding 500 rpm) to prevent entraining air for a minimum 5 minutes for a 5 gallon pail, and 3 minutes for a 1 gallon can.

**Warning:** Product is thixotropic and will thin after mixing, wait 1 hour for product to re-thicken before applying.

#### **Application:**

Read all instructions thoroughly prior to installation.

- ❖ Ensure substrate and ambient temperatures are between 40°F and 95°F (4°C and 35°C) before application. Do not apply if freezing temperatures are expected within 24 hours.

Cantex Roller/Brush<sup>®</sup> can be applied using a min. 3/4" nap paint roller or industrial paint brush. Apply by roller or brush at a rate of 50 ft<sup>2</sup> per gallon (30 mils). Apply in two coats to achieve 60 mils total thickness. To apply using an appropriate spray pump consult with Cantex Coatings Ltd.

Coverage: ~25 ft<sup>2</sup>/gal @ 60 mils DFT

#### **Curing:**

Cantex Roller/Brush<sup>®</sup> will begin curing immediately upon application. Full cure occurs within 72 hours at 70°F (21°C) with a relative humidity of 50%. Humidity can significantly impact cure times.

#### **Limitations:**

- ❖ Do not bridge moving cracks or joints larger than 1/16". Use "tape & seal" method in conjunction with Cantex Trowel Grade<sup>®</sup>
- ❖ Do not add admixtures or extend with aggregate
- ❖ Protect from freezing for 24 hours after application. If product freezes before full cure it may become necessary to recoat if cracking occurs within the membrane.



Cantex Coatings Ltd.  
 424 Rennie Street  
 Hamilton, ON L8H3P5  
 1-888-663-CNTX (2689)  
 www.cantexcoatings.com

**Roller/Brush Rubber<sup>®</sup>**  
**Cold Fluid Applied Rubber Membrane System**

**Technical Datasheet**

**Clean-up:**

Promptly wash hands in baby oil. Clean tools and equipment with Mineral spirits before material dries. Cured material must be removed mechanically.

**Packaging:**

Cantex Roller/Brush<sup>®</sup> is available in 5 gallon pails and/or 55 Gallon (US) drums – by special order only.

**Shelf Life:**

12 months in unopened, original packaging

**Note:**

Proper application is the responsibility of the user. Field visits by Cantex personnel are for the purpose of making technical recommendations and not for supervising or providing quality control on-site.

**Safety:**

Refer to current SDS. For commercial use only. Avoid contact with skin and eyes. Wear rubber gloves and safety goggles during mixing and application. After contact with skin, wash with plenty of water. In case of eye contact, rinse immediately with plenty of water for 15 minutes and seek medical advice.

**LIMITED WARRANTY:**

Cantex Coatings Ltd. warrants this product for a period of one year from the date of installation to be manufactured free of defects and to be consistent with its technical properties as stated in our current Technical Data Sheet. This product must be used as directed and within its stated shelf life. CANTEX COATINGS LTD. will replace or at our discretion refund the purchase price of any product, excluding cost of labor, which is proven to be defective. Our product recommendations are based on industry standards and testing procedures. It is the buyer's obligation to test the suitability of the product for an intended use prior to using it. We assume no warranties written, expressed or implied as to any specific methods of application or use of the product. Cantex Coatings Ltd. MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESS OR IMPLIED. CANTEX COATINGS LTD. shall not be liable for damages of any sort including remote or consequential damages, down time, or delay. Any claim for a defective product must be filed within 30 days of discovery of a problem, and must be submitted with written proof of purchase.

<b>Technical Properties</b>	
Physical State	Liquid
Colour	Brownish-black
Hydrostatic Resistance (ASTM 5751-00)	>350 psi Positive and negative side
Resistance to puncture (ASTM E154-99 Section 10)	> 34 N
Elongation at break @ -5.6°C (ASTM D4 12-98a(2000))	480%
Elongation at room temperature (ASTM D4 12-98a (2000))	1200%
Low temperature brittleness @ 15°C (ASTM D746-04)	Passed
Low temperature flexibility (ASTM D1970-01)	Passed
Water absorption (ASTM D570-98)	< 1.4
Perm rating (ASTM E96)	0.12 grains/hr ft <sup>2</sup>
Fire rating (ASTM E109-94)	Class C
All data are averages of several tests under laboratory conditions. In practice climatic variations such as temperature, humidity and porosity of substrate may affect these values	
<b>Packaging &amp; Coverage Rate:</b>	
Available in 5 gal. pails	approx. yield 125 ft <sup>2</sup> @ 60 mils DFT

**For Professional Use Only**  
**KEEP OUT OF REACH OF CHILDREN**